

AMBIENTA SRL
Ms. Francesca Maria Locatelli
Via Donizetti, 109 - Area Geller D 1A
24030 BREMBATE SOPRA
Italië



Your notice of
30-05-2018

Your reference

Date
21-06-2018

Analysis Report 18.03126.01

Required tests :

EN 13773 (2003)

| Identification number | Information given by the client | Date of receipt |
|-----------------------|---------------------------------|-----------------|
| T1813059 | FILET | 30-05-2018 |

Mieke Demeyer

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T1813059 - FILET

Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.

Date of ending the test 04-06-2018
Standard used EN 1101 (1995) + A1 (2005)
Product standard EN 13773 (2003)
Deviation from the standard -
Conditioning 20°C, relative humidity 65%
Ignition Bottom edge

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

| Flame application time (s) | Cases of ignition | Cases of non-ignition |
|----------------------------|-------------------|-----------------------|
| 1 | 0 | 1 |
| 2 | 0 | 1 |
| 3 | 0 | 1 |
| 4 | 0 | 1 |
| 5 | 0 | 1 |
| 10 | 0 | 1 |
| 15 | 0 | 1 |
| 20 | 0 | 5 |

The mean of the recorded times at which ignition was observed is calculated

No ignition within 20 s




Width

| Flame application time (s) | Cases of ignition | Cases of non-ignition |
|----------------------------|-------------------|-----------------------|
| 1 | 0 | 1 |
| 2 | 0 | 1 |
| 3 | 0 | 1 |
| 4 | 0 | 1 |
| 5 | 0 | 1 |
| 10 | 0 | 1 |
| 15 | 0 | 1 |
| 20 | 0 | 5 |

The mean of the recorded times at which ignition was observed is calculated

No ignition within 20 s





Reference: T1813059 - FILET

Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.

Date of ending the test 07-06-2018
Standard used EN 13772 (2011)
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

| | Face A | Face B | Face A | Face A |
|--|--------|--------|--------|--------|
| Severance 1 st thread | no | no | no | no |
| Severance 2 nd thread | no | no | no | no |
| Severance 3 rd thread | no | no | no | no |
| Time to sever 3 rd thread (s) | / | / | / | / |
| Destroyed length (mm) | 115 | 115 | 115 | 120 |
| Flaming debris | no | no | no | no |

Width

| | Face A | Face B | Face A | Face A |
|--|--------|--------|--------|--------|
| Severance 1 st thread | no | no | no | no |
| Severance 2 nd thread | no | no | no | no |
| Severance 3 rd thread | no | no | no | no |
| Time to sever 3 rd thread (s) | / | / | / | / |
| Destroyed length (mm) | 115 | 115 | 115 | 150 |
| Flaming debris | no | no | no | no |

Classification in accordance with EN 13773 Class 1

